## Modcell®

### **Technical Data Sheet**

# LK20M

### Hydroxypropyl methyl cellulose HPMC

#### **Product Description**

Hydroxypropyl Methyl Cellulose Ether LK20M is multifunctional additive for ready-mixes and dry-mix products. It is a high efficient water retention agent, thickener, stabilizer, adhesive, film-forming agent in building materials.

Product Specification	
Appearance	White freely flowing powder
Bulk density	19~38(0.5~0.7) (lb/ft 3) (g/cm 3)
Methyl content	19.0-24.0 (%)
Hydroxypropyl content	4.0-12.0 (%)
Gelling temperature	70-90 (°C)
Moisture content	≤5.0 (%)
PH Value	5.0-9.0
Residue(Ash)	≤5.0 (%)
Viscosity(2%solution)	25,000 (mPa.s, Brookfield 20rpm 20°CSolution) - 10%,+209
Package	25 (Kg/bag)
Applications	
<ul> <li>mortar for insulation mortar</li> </ul>	
<ul> <li>interior/exterior wall putty</li> </ul>	
<ul> <li>Ceramic tile adhesive</li> </ul>	
<ul> <li>Common mortar</li> </ul>	
Benefits	
<ul> <li>Standard open time</li> </ul>	
<ul> <li>Standard slip resistance</li> </ul>	
<ul> <li>Standard water retention</li> </ul>	
<ul> <li>Sufficient tensile adhesion strength</li> </ul>	
➤ Improve workability	
Announcements	
•Storage and delivery	
It should be stored and delivered under dry a	and clean conditions in its original package form and away from hea

After the package is opened for production, tight re-sealing must be taken to avoid ingress of moisture.

•Shelf life



The warranty period is two years. Use it as early as possible under high temperature and humidity, so as not to increase the probability of caking.

Product safety

Hydroxypropyl methyl cellulose HPMC LK20M does not belong to hazardous material. Further information on safety aspects is given in Material Safety Data Sheet.

#### Statement:

All of data, suggestions, and proposals presented here are based on our current knowledge and experience in raw materials and application technologies, which do not exclude the responsibility of users to scrutinize the quality of all received products. Because we are out of control of quality in users' raw materials, production and application methods, service conditions as well as local standards, our suggestions and proposals do not imply any guarantee and promise for end product's quality. The users should be responsible for formulation adjustment according to real conditions to meet project quality requirements.

Longou International Business(Shanghai) Co., Ltd. & Puyang Longou Biotechnology Development Co., Ltd.

Address: Building 38, Room 2002, 700 Liquan Road, Putuo District, Shanghai, China

Tel: +86-021-62503072 (Shanghai) +86-0393-6975188 (Puyang )

Fax: +86-021-62503097 (Shanghai) +86-0393-6905188 (Puyang )

Web: www.longouchem.com www.longoucell.com

